

PALL-X GOLD

PALLMANN® Pall-X GOLD is a 2-component waterborne hardwood floor finish with unmatched durability and chemical resistance. It is ideal for high-wear commercial and residential applications.

Features

- Unmatched durability
- Available in Matte, Satin, and Semi-Gloss
- Superior flow and leveling
- Exceptional build
- Fast drying and curing
- Low odor
- Not UV sensitive

Benefits

- Ideal for high-wear commercial and residential applications
- Most popular sheens
- Very forgiving, easy to apply
- Deep, rich, finished appearance
- Allows for light foot traffic in 3-4 hours, fully cured in 4 days
- Non-offensive on jobsites
- Will not amber over time

Technical Data

Packaging: Plastic containers Unit Size: Component A: 1 U.S. gallon Component B: 0.1 U.S. gallon Color: Milky white when wet, clear when dry Odor: Solids: Sheens: Gloss Level (60°): **VOC Content:** Stability: Clarity: Coverage Rate: Pot Life: Drying Time: Foot Traffic: Fully Cured: Leveling:

Non-offending 36% for Satin Matte, satin, semi-gloss 10 GU Matte, 24 GU Satin, 35 GU Semi-Gloss VOC of mixed components A&B does not exceed 200 grams per liter Min. 12 months* Clear when dry, non-yellowing (not UV sensitive) Approx. 450-500 sq ft per gallon Approx. 4 hours after Comp B is added** Approx. 2 hours** After approx. 3-4 hours** After approx. 3 days** Superior Excellent

T-Bar applicator, brush, cut-in pad or roller.

Storage & Working Temp:

Defoaming:

Application Tools:

Store between 50° and 70°F (10-20°C)* and apply at room temperature 65-75°F (18-25°C) for best results**

* Under optimal storage conditions

** Under optimal application conditions





Fully Cured In 3 Days

PALL-X GOLD Directions for Use:

BEFORE USING READ ALL DIRECTIONS AND SAFETY DATA SHEET (SDS). FOR PROFESSIONAL USE ONLY. This product meets or exceeds all state and federal clean air quality standards and reflects our commitment to personal health, indoor air quality and the environment. DO NOT THIN this product. Call the PALLMANN[®] division of Uzin Utz North America before using for technical advice if needed (1-866-505-4810).

First Aid

In case of skin contact, wash thoroughly with soap and water. For eye contact, flush immediately with large amounts of water for at least 15 minutes and get medical attention. If swallowed, do not induce vomiting. Get medical attention immediately. Refer to safety information on product label as well as our Safety Data Sheet (SDS). When fully cured this product presents no physiological or ecological risks.

Preparation

TO ENSURE COMPATIBILITY AND DESIRED RESULTS TEST PRODUCT ON A SAMPLE BOARD OR IN AN INCONSPICUOUS LOCATION. Floor must be free of all contaminants, such as wax, oily residue, or silicone. Stain, sealer, and finish results may vary widely depending on the wood species, especially on oily and resinous exotic species. PALLMANN® PALL-X BOND is the recommended system when recoating factory prefinished floors. Sand and prepare the wood floor in accordance to NWFA (National Wood Flooring Association) sanding guidelines. More information on these guidelines can be found at www.nwfa. org. If floor is stained, assure that stain is thoroughly dried in accordance with stain manufacture label directions for the product before applying sealer coat. Failure to do so may result in lack of adhesion of the sealer and / or finish coats. Finish may be applied directly to stain. For best results use a PALLMANN® SEALER over stain prior to application of finish. The PALLMANN® Finishing system is a three coat system. 1-Coat of PALLMANN® SEALER, 2-Coats PALLMANN® FINISH.

Recommended Applicators: T-Bar, cut-in-pad, PALLMANN® Waterborne Roller, brush. Use seperate, clean applicators for both sealer and finish applications.

Use seperate, clean applicators for both sealer and finish applications.

Finishing

Shake Component A vigorously for 30 seconds before adding Component B. Then add Component B and shake IMMEDIATELY for an additional 60 seconds. One bottle of hardener will activate 1 gallon of PALL-X 98 finish. **NOTE: Let combined product sit for 5 minutes prior to application for proper activation and optimal flow and leveling.** Failure to shake, mix and properly activate finish products may result in streaking when the finish is dry. DO NOT ADD WATER TO FINISH.

T-Bar Application:

Pour a 4" wide line of finish along the starting wall. Using a clean, pre-dampened T-Bar applicator draw the applicator in the direction of the grain of wood at a slight angle. While keeping the wet edge in the middle of the T-Bar move the finish puddle with the grain of wood wall to wall. At the end of each run turn the applicator towards you and pad out the applicator parallel to the wet edge. Feather out all

Uzin Utz NORTH AMERICA

PALLMANN I A Brand of Uzin Utz Group Aurora, CO 80011 USA | Phone: 720. 374.4810 pallmann.us@uzin-utz.com I pallmann.us turns, and touch up any missed areas if seen right away. NOTE: Always move T-Bar with the grain of the wood.

Rolling Application:

Pour a 4" wide line of finish along the starting wall. Using a clean, pre-dampened PALLMANN[®] Waterborne Roller draw the applicator through the finish towards you pulling away from the wall approximately 4". Move the applicator over half the length of the applicator and repeat the process from wall to wall. Pour a new line of finish into the finish that is on the floor, and repeat process. Touch up any missed areas if seen right away. It is important to maintain the coverage rate of 450 – 500 sq. ft. per gallon, and to not over work the finish as you are applying it. Failure to adhere to either of these recommendations could result in the finish drying too quickly, bubbles, streaking, visible lap lines, or sheen variances.

Intercoat Abrasion

If more than 24 hours has elapsed since the last finish coat was applied, the surface **must** be abraded prior to applying the next coat of finish in order to ensure adhesion. Use a 120 - 150 grit screen or sanding strips for best results. Vacuum and tack thoroughly with a lightly water-dampened lint-free cloth after abrading.

Curing

The curing process takes approximately 3 days. Wait 3 days before replacing rugs and mats. The floor may be walked on after 24 hours, but the floor is susceptible to scuffing or marring prior to fully curing. Do not use cleaner during this 3 day curing time. Use only a dry, untreated PALLMANN® MICROFIBER DUSTING PAD or lint-free tacking cloth during the first week of use. DO NOT use abrasive, acidic or harsh cleaners.

Clean-Up

Tools and applicators should be cleaned with water.

Maintenance

Put walk-off mats at all entrance doorways to keep out excessive dirt and grit. Sweep or vacuum as needed to clean floors with PALLMANN® MICROFIBER MOP. The recommended cleaner is PALLMANN® HARDWOOD FLOOR CLEANER.

Storage

PALL-X GOLD has up to a 4 hour pot life after hardener has been added. Opened containers should be securely recapped and stored in cool conditions (below 75° F) until re-used. KEEP FROM FREEZING. Finish in previously opened containers should be strained prior to use to eliminate any material coagulation that may occur.

Disposal

Dispose of any unused/unwanted product or containers in accordance with local, state and federal regulations.



Rev 7/11/19