



PALL-X FILLER

Waterborne fiber-reinforced wood filler compound for wood floors

Description

PALLMANN® PALL-X FILLER is a patented fiber-reinforced wood filler compound. Suitable for solid strip, plank, engineered or parquet flooring. PALL-X FILLER uses sanding dust to create the perfect color match. PALL-X FILLER is rated for radiant heat floor systems and should be used where color-matching, stability, wide joints, and adhesion are vital.

Features

- Fiber-reinforced
- Mixes with sanding dust from floor
- No-clog formula
- Fast drying

Benefits

- Holds well in gaps
- Natural color match
- Will not load abrasives
- Less downtime

Technical Data

Packaging:	1 U.S. plastic gallon (3.78 Liters)
Color:	Yellow when wet, color-matched to species when dry
Stability:	At least 12 months
Mixing Ratio:	Blend to a paste consistency that can be trowel applied
Working Temp.:	65 – 75 °F (18 – 25 °C) for optimum performance
Coverage Rate:	Approx. 400 sq. ft. per gallon, depending on floor condition
Ready for Sanding:	20 – 25 minutes
Storage:	Store between 50 – 70 °F (10 – 20 °C). Keep from freezing.

Directions for Use

Shake product well prior to mixing with 80 – 100 grit edger or buffer sanding dust. Pour the PALL-X FILLER into a 'crater' of sanding dust on the floor to be filled. Using a stainless steel trowel (Item #12506), blend the liquid with the dust to achieve a trowelable paste consistency. Trowel apply to the floor, filling all joints and gaps.

NOTE: From time to time it will be necessary to add more PALL-X FILLER to the mix on the floor to maintain a paste-like consistency. PALL-X FILLER may also be mixed with sanding dust in a bucket prior to trowel application.

Important Notes

The filling application should be made before the final cut with the belt or drum sander. The floor can normally be sanded 20 to 25 minutes after filling. High humidity and / or low temperature conditions may extend the dry time while increased ventilation and airflow may reduce dry time. PALL-X FILLER must be removed with a belt sander or the PALLMANN SPIDER. Do not attempt to remove PALL-X FILLER with only a single drive plate rotary buffer. To ensure proper color match, test filler, stain and finish in an inconspicuous area. Do not use with bamboo floors.

Clean Up

Tools and applicators should be cleaned with water.

Storage

Minimum 12 months in original packaging when stored under normal conditions (50 – 70 °F / 10 – 20 °C). Tightly reseal opened containers. Keep from freezing.



Uzin Utz
NORTH AMERICA

PALLMANN | A Brand of Uzin Utz Group
Aurora, CO 80011 USA | Phone: 720. 374.4810
pallmann.us@uzin-utz.com | us.pallmann.net



PALLMANN®
wood floors. protected